


FlexiShield

Paint Protection Film

www.FlexiShield.com



What is Paint Protection Film?

Paint Protection Film (PPF) is a soft film material made from **thermoplastic polyurethane (TPU)**. Paint Protection Film is specifically cut to fit the make and model of any car - using FlexiShield's RAP 2.0 software - and is applied to the car exteriors and sometimes interiors. TPU is incredibly tough and durable, and possesses a "self-healing" property that allows it to return to its original shape when stretched, distressed, or scratched.

PPF can also be designed to be **water repellent, stain resistant, and transparently glossy or satined**. PPF can maintain and increase the value of a vehicle, not only by protecting its paint and finishings, but also by enhancing the appearance of the vehicle's surface.

Because of its superior technology and in-house manufacturing FlexiShield is the ultimate choice in Paint Protection Film, and remains the established preference for the most demanding car owners and installers.

A brand of:



FFS

COVERAGE YOU CAN COUNT ON!



100% US manufactured,
developed and tested under the
blazing Arizona sun.

FlexiShield WSH

Protect your valued assets with
FlexiShield WSH

FlexiShield's 8,0mil (203 μ) thick WSH PPF is engineered to provide all-around surface protection for high-value cars, yachts, architectural interiors, and many other personal and commercial assets. FlexiShield WSH has been formulated for optimum self-healing performance, durability, and versatility of installation.



Well-balanced, all-around
protection.



Over one decade of field
testing in climates all
around the world.



Optimum thickness and
flexibility for the broadest
versatility of installation.

With a decade of field testing under all
weather conditions - from the scorching
Arizona desert to the frozen fjords of Norway
- FlexiShield WSH remains the go-to option for
the most discerning PPF installers.

8.0mil (203 μ)
High-gloss
10-year warranty

WSH SPECIFICATIONS

Total Thickness	8.0 mil (203 μ)*	PCE Thickness Gauge
Top Coat	0.5 mil (13 μ)	
Polyurethane Film	6.5 mil (165 μ)*	
Adhesive	1.0 mil (25 μ)	

UV Accelerating Test - 3000 Hours, 105°F - Pass
(Equivalent to 5 years)

TPU Haze (Clarity) Δ	1.20 %	ASTM D1003-1 Original 0.8
Yellowing Δ	< 1.20 %	ASTM D1925-70
Self Healing Δ	Pass	Lab Testing
Cold Slam - Cracking or Peeling	Pass	TPJLR.52.055
Elongation (at break MD)	>350%	ASTM 6775-13
Stain Resistance (Unleaded gasoline, Kerosene)	No cosmetic defects	Lab Testing
20° Gloss (Stainless steel surface)	>96 GU	Gloss Meter 20°
Chip Resistance Gravelometer	No damage on paint	ASTM D3170

Adhesion Performance

Peel Adhesion 180 Degree Peel 1.0 mil coating Paint Surface	449.0 N/m	41 oz/in	20 minutes at room temperature
	481.0 N/m	44 oz/in	24 hours at room temperature
	514.0 N/m	47 oz/in	1 week at room temperature
	689.0 N/m	63 oz/in	1 week at 160°F/70°C
	765.0 N/m	70 oz/in	1 week at 95°F/ 35°C, 95% RH

* Thickness tolerance: Maximum +/- 8%. Data provided by TPU manufacturer.

FlexiShield USA
HQ & Manufacturing

+1 (866) 312 9909

FlexiShield EU
Distribution Office

+31 6 3458 3582

FlexiShield ME
Distribution Office

+971 50 555 4246

www.FlexiShieldUSA.com
contact@reflektech.com
280 N Roosevelt Ave
Chandler AZ 85226 USA

www.FlexiShieldEU.com
salesEU@reflektech.com
Marconistraat 70H
Gouda 2809PE NL

www.FlexiShieldME.com
salesME@reflektech.com
WH 36/D 06 ABA Avenue
Al Gouz 02, Dubai, UAE

intertek
Total Quality. Assured.



SGS



AMERICAN
SOCIETY OF
INTERIOR
DESIGNERS

INTERNATIONAL
WINDOW FILM
ASSOCIATION



NGA
NATIONAL GLASS ASSOCIATION



ISO 9001
CERTIFIED

